

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
13 March 2003 (13.03.2003)

PCT

(10) International Publication Number  
**WO 03/020784 A1**

(51) International Patent Classification<sup>7</sup>: **C08G 18/34**

(21) International Application Number: **PCT/EP02/09541**

(22) International Filing Date: **27 August 2002 (27.08.2002)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:  
**01830553.2 30 August 2001 (30.08.2001) EP**

(71) Applicant (*for all designated States except US*): **HUNTS-  
MAN INTERNATIONAL LLC [US/US]; 500 Huntsman  
Way, Salt Lake City, UT 84108 (US).**

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **KUESTER, Joern  
[DE/IT]; Via Rosselli 42, I-21100 Varese (IT). FARE,  
Roberto [IT/IT]; Via F. Tamagno 8, I-21100 Varese (IT).  
FERGUSON, David, Alexander [GB/GB]; Killarney,  
Street Road, Glastonbury, Somerset BA6 9EG (GB).**

(74) Agents: **SWINNEN, Anne, Marie et al.; Huntsman (Eu-  
rope) BVBA, Intellectual Property Department, Everslaan  
45, B-3078 Everberg (BE).**

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **PROCESS FOR MAKING RIGID URETHANE-MODIFIED POLYISOCYANURATE FOAMS**

(57) Abstract: Process for preparing rigid urethane-modified polyisocyanurate foams from polyisocyanates and polyfunctional isocyanate-reactive components in the presence of a blowing agent, a metal salt trimerisation catalyst and a functionalised carboxylic acid.

WO 03/020784 A1

## DESCRIPTION

## PROCESS FOR MAKING RIGID URETHANE-MODIFIED POLYISOCYANURATE FOAMS

5

This invention relates to processes for the preparation of rigid urethane-modified polyisocyanurate foams, to foams prepared thereby and to compositions useful in said processes.

10 Rigid urethane-modified polyisocyanurate (PIR) foams are in general prepared by reacting a stoichiometric excess of polyisocyanate with isocyanate-reactive compounds (usually a polyol) in the presence of a blowing agent, surfactants and catalysts. One use of such foams is as a thermal insulation medium as, for example, in buildings.

15 Urethane-modified polyisocyanurate foams exhibit better fire retardancy, reduced smoke emission in fire situations and greater thermal stability than polyurethane foams in general, due to the presence of the isocyanurate groups.

20 Higher index PIR foams are increasingly desirable in construction applications due to more stringent fire regulations and the need for low smoke systems.

However it has shown very difficult to achieve good isocyanurate conversion with slow reacting foam systems as is the case in thick (20 cm) lamination panels and in discontinuous panels.

25 Another disadvantage of PIR foams in general is their poor adhesion to facer materials in building panels.

It is an object of the present invention to provide PIR systems that give good isocyanurate conversion, especially at slow speeds (string time  $\pm$  90 seconds).

30

The present invention involves a method for making rigid urethane-modified polyisocyanurate foams from polyisocyanates and polyfunctional isocyanate-reactive components in the presence of blowing agents and in the presence of a trimerisation catalyst and a carboxylic acid.

35

A good isocyanurate conversion can be achieved in lamination systems over a range of panel thicknesses, using the same polyol masterbatch. The slow reaction speed required

for high thickness panels is achieved by employing a carboxylic acid together with a trimerisation catalyst.

Good isocyanurate conversion leads to good fire properties. At the same time compressive strength and dimensional stability of the foam is optimised.

5

But also in faster systems (string time between 30 and 40 seconds) the use of a carboxylic acid in combination with a trimerisation catalyst leads to improved processing for PIR foams and a higher isocyanurate conversion.

10 The carboxylic acids useful in the practice of the present invention generally have molecular weights below about 250, preferably below 200.

In a preferred embodiment of the present invention the carboxylic acids have molecular weights in the range 50 to 150.

15 Preferably the carboxylic acids to be used in the present invention have a pKa value in water of between 1 and 5.5, more preferably between 1.2 and 5, most preferably between 1.8 and 4.8.

20 In a preferred embodiment of the present invention functionalised carboxylic acids are used; these are organic carboxylic acids containing at least one additional OH, COOH, SH, NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen functional group, wherein R is an alkyl, cycloalkyl or aryl group. Introducing an unsaturation also qualifies as a functional group.

Preferably the carboxylic acid is functionalised in  $\alpha$  or  $\beta$  position with respect to the carboxyl group.

25

Functionalised carboxylic acids suitable for use in the present invention have the general formula  $X_n - R' - \text{COOH}$  wherein X is OH, COOH, SH, NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen and R' is an at least divalent hydrocarbon moiety, typically an at least divalent linear or branched aliphatic hydrocarbon moiety and/or an at least divalent alicyclic or aromatic hydrocarbon moiety, n is an integer having a value of at least 1 and allows for mono and polyfunctional substitution on the hydrocarbon moiety.

30

The "at least divalent hydrocarbon moiety" can be a saturated or unsaturated moiety of 1 to 20 carbon atoms, including a linear aliphatic moiety, a branched aliphatic moiety, an alicyclic moiety or an aromatic moiety. Stated otherwise, R' can, for example, be a linear or branched alkylene group of 1 to 10 carbon atoms, a cyclic alkylene group of 4 to 10 carbon atoms, or an arylene, an alkarylene or an ararylene group of 6 to 20 carbon atoms. Specific non-limiting

35

examples of suitable hydrocarbon moieties are methylene, ethylene, n-propylene, isopropylene, n-butylene, isobutylene, n-amylene, n-decylene, 2-ethylhexylene, o-, m-, p-phenylene, ethyl-p-phenylene, 2,5-naphthylene, p,p'-biphenylene, cyclopentylene, cycloheptylene, xylylene, 1,4-dimethylenephenylene and the like. While above-noted radicals have two available substitution sites, at least one for a carboxyl group and one for an additional OH, COOH, SH, NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen group, it is contemplated that additional hydrogens on the hydrocarbon could be replaced with further carboxyl and/or OH, SH, NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen groups.

- 10 Preferably X is OH or COOH, n is 1, R' is a linear or branched aliphatic or aromatic hydrocarbon having 2 to 6 carbon atoms

The following carboxylic acids are illustrative of compounds suitable for practicing the present invention: citric acid, dimethylolpropionic acid, bis-(hydroxymethyl)propionic acid, bishydroxypropionic acid, salicylic acid, m-hydroxy benzoic acid, p-hydroxy benzoic acid, dihydroxybenzoic acid, glycolic acid,  $\beta$ -hydroxybutyric acid, cresotic acid, 3-hydroxy-2-naphthoic acid, lactic acid, tartaric acid, malic acid, maleic acid, resorcylic acid, hydroferulic acid, glycine, alanine, acetic acid, mercaptoacetic acid and the like.

- 20 Most preferred carboxylic acids are lactic acid, acetic acid, malic acid, maleic acid and salicylic acid.

At least one of said carboxylic acids is used; mixtures of two or more of these acids can be used as well.

25

The carboxylic acid is generally used in an amount ranging from 0.05 to 5 % by weight based on the isocyanate-reactive composition, preferably about 0.1 % to 2 %.

- 30 Any compound that catalyses the isocyanate trimerisation reaction can be used as trimerisation catalyst such as tertiary amines, triazines and most preferably metal salt trimerisation catalysts.

Examples of suitable metal salt trimerisation catalysts are alkali metal salts of organic carboxylic acids. Preferred alkali metals are potassium and sodium. And preferred carboxylic acids are acetic acid and 2-ethylhexanoic acid.

Preferred metal salt trimerisation catalysts are potassium acetate (commercially available as Polycat 46 from Air Products and Catalyst LB from Huntsman Polyurethanes) and, most preferably, potassium 2-ethylhexanoate (commercially available as Dabco K15 from Air Products).

Two or more different metal salt trimerisation catalysts can be used in the process of the present invention.

The metal salt trimerisation catalyst is generally used in an amount ranging from 0.5 to 5 % by weight based on the isocyanate-reactive composition, preferably about 1 to 3 %.

In general an almost stoichiometric ratio of acid/metal salt is used, especially if Dabco K15 or Catalyst LB are used as metal salt trimerisation catalyst.

A particularly preferred combination of carboxylic acid and metal salt trimerisation catalyst is lactic acid together with Dabco K15.

20

In addition to this metal salt trimerisation catalyst other types of trimerisation catalysts and urethane catalysts can be used. Examples of these additional catalysts include dimethylcyclohexylamine, triethylamine, pentamethylenediethylenetriamine, tris (dimethylamino-propyl) hydrotriazine (commercially available as Jeffcat TR 90 from Huntsman Performance Chemicals), dimethylbenzylamine (commercially available as Jeffcat BDMA from Huntsman Performance Chemicals). They are used in amounts ranging from 0.5 to 8 % by weight based on the isocyanate-reactive composition. In general the total amount of trimerisation catalyst is between 0.4 and 4.5 % and the total amount of urethane catalyst ranges from 0.1 to 3.5 % by weight based on the isocyanate-reactive composition.

30

The reaction is typically carried out an isocyanate index of 150 to 450 %, preferably at an isocyanate index of 180 to 300 %.

The term isocyanate index as used herein is meant to be the molar ratio of NCO-groups over reactive hydrogen atoms present in the foam formulation, given as a percentage.

5 In terms of "excess isocyanate", which is the weight percentage of isocyanate in the total formulation which is not used for the OH/NCO reaction, this means between 10 and 60 %.

The rigid urethane-modified polyisocyanurate foam produced according to the process of the present invention generally is closed-celled, i.e. the open cell content is less than 20 %.

10 Suitable isocyanate-reactive compounds to be used in the process of the present invention include any of those known in the art for the preparation of rigid polyurethane or urethane-modified polyisocyanurate foams. Of particular importance for the preparation of rigid foams are polyols and polyol mixtures having average hydroxyl numbers of from 160 to 1000, especially from 200 to 700 mg KOH/g, and hydroxyl functionalities of from 2 to 8, especially  
15 from 2 to 6. Suitable polyols have been fully described in the prior art and include reaction products of alkylene oxides, for example ethylene oxide and/or propylene oxide, with initiators containing from 2 to 8 active hydrogen atoms per molecule. Suitable initiators include: polyols, for example glycerol, trimethylolpropane, triethanolamine, pentaerythritol, sorbitol and sucrose; polyamines, for example ethylene diamine, tolylene diamine (TDA),  
20 diaminodiphenylmethane (DADPM) and polymethylene polyphenylene polyamines; and aminoalcohols, for example ethanolamine and diethanolamine; and mixtures of such initiators. Other suitable polymeric polyols include polyesters obtained by the condensation of appropriate proportions of glycols and higher functionality polyols with dicarboxylic or polycarboxylic acids, DMT-scrap or digestion of PET by glycols. Still further suitable  
25 polymeric polyols include hydroxyl-terminated polythioethers, polyamides, polyesteramides, polycarbonates, polyacetals, polyolefins and polysiloxanes.

Preferably the isocyanate-reactive composition contains at least 30 wt%, preferably at least 60 wt% of polyester polyols.

30 In a particularly preferred embodiment of the present invention almost all of the isocyanate-reactive compounds are polyester polyols.

Suitable organic polyisocyanates for use in the process of the present invention include any of those known in the art for the preparation of rigid polyurethane or urethane-modified polyisocyanurate foams, and in particular the aromatic polyisocyanates such as diphenylmethane diisocyanate in the form of its 2,4'-, 2,2'- and 4,4'-isomers and mixtures thereof, the mixtures of diphenylmethane diisocyanates (MDI) and oligomers thereof known in the art as "crude" or polymeric MDI (polymethylene polyphenylene polyisocyanates) having an isocyanate functionality of greater than 2, toluene diisocyanate in the form of its 2,4- and 2,6-isomers and mixtures thereof, 1,5-naphthalene diisocyanate and 1,4-diisocyanatobenzene. Other organic polyisocyanates, which may be mentioned, include the aliphatic diisocyanates such as isophorone diisocyanate, 1,6-diisocyanatohexane and 4,4'-diisocyanatodicyclohexylmethane.

The quantities of the polyisocyanate compositions and the polyfunctional isocyanate-reactive compositions to be reacted will depend upon the nature of the rigid polyurethane or urethane-modified polyisocyanurate foam to be produced and will be readily determined by those skilled in the art.

Any of the physical blowing agents known for the production of rigid polyurethane or urethane-modified polyisocyanurate foam can be used in the process of the present invention. Examples of these include dialkyl ethers, cycloalkylene ethers and ketones, fluorinated ethers, chlorofluorocarbons, perfluorinated hydrocarbons, hydrochlorofluorocarbons, hydrofluorocarbons, and in particular hydrocarbons.

Examples of suitable hydrochlorofluorocarbons include 1-chloro-1,2-difluoroethane, 1-chloro-2,2-difluoroethane, 1-chloro-1,1-difluoroethane, 1,1-dichloro-1-fluoroethane and monochlorodifluoromethane.

Examples of suitable hydrofluorocarbons include 1,1,1,2-tetrafluoroethane (HFC 134a), 1,1,2,2-tetrafluoroethane, trifluoromethane, heptafluoropropane, 1,1,1-trifluoroethane, 1,1,2-trifluoroethane, 1,1,1,2,2-pentafluoropropane, 1,1,1,3-tetrafluoropropane, 1,1,1,3,3-pentafluoropropane (HFC 245fa), 1,1,3,3,3-pentafluoropropane, 1,1,1,3,3-pentafluoro-n-butane (HFC 365mfc), 1,1,1,4,4,4-hexafluoro-n-butane, 1,1,1,2,3,3,3-heptafluoropropane (HFC 227ea) and mixtures of any of the above.

Suitable hydrocarbon blowing agents include lower aliphatic or cyclic, linear or branched hydrocarbons such as alkanes, alkenes and cycloalkanes, preferably having from 4 to 8 carbon atoms. Specific examples include n-butane, iso-butane, 2,3-dimethylbutane, cyclobutane, n-pentane, iso-pentane, technical grade pentane mixtures, cyclopentane, methylcyclopentane, neopentane, n-hexane, iso-hexane, n-heptane, iso-heptane, cyclohexane, methylcyclohexane, 1-pentene, 2-methylbutene, 3-methylbutene, 1-hexene and any mixture of the above. Preferred hydrocarbons are n-butane, iso-butane, cyclopentane, n-pentane and isopentane and any mixture thereof, in particular mixtures of n-pentane and isopentane (preferred weight ratio 3:8), mixtures of cyclopentane and isobutane (preferred weight ratio 8:3), mixtures of cyclopentane and n-butane and mixtures of cyclopentane and iso- or n-pentane (preferred weight ratio between 6:4 and 8:2).

Generally water or other carbon dioxide-evolving compounds are used together with the physical blowing agents. Where water is used as chemical co-blowing agent typical amounts are in the range from 0.2 to 5 %, preferably from 0.5 to 3 % by weight based on the isocyanate-reactive compound.

Water can also be used as the sole blowing agent with no additional physical blowing agent being present.

Since some of the acids such as lactic acid also show a blowing capacity the water levels can be reduced (to levels below 1 %) which improves cure and adhesion of the foam.

The total quantity of blowing agent to be used in a reaction system for producing cellular polymeric materials will be readily determined by those skilled in the art, but will typically be from 2 to 25 % by weight based on the total reaction system.

Preferred blowing agents are water and/or hydrocarbons and/or hydrofluorocarbons.

In addition to the polyisocyanate and polyfunctional isocyanate-reactive compositions and the blowing agents, the foam-forming reaction mixture will commonly contain one or more other auxiliaries or additives conventional to formulations for the production of rigid polyurethane and urethane-modified polyisocyanurate foams. Such optional additives include crosslinking agents, for examples low molecular weight polyols such as triethanolamine, surfactants, fire



retardants, for example halogenated alkyl phosphates such as tris chloropropyl phosphate, and fillers such as carbon black.

5 In particular in the present invention additives can be used to further improve the adhesion of the foam to the facer material. These include triethylphosphate, mono- and polyethyleneglycol and propylene carbonate, either alone or mixtures thereof.

10 In operating the process for making rigid foams according to the invention, the known one-shot, prepolymer or semi-prepolymer techniques may be used together with conventional mixing methods.

15 It is convenient in many applications to provide the components for polyurethane production in pre-blended formulations based on each of the primary polyisocyanate and isocyanate-reactive components. In particular, many reaction systems employ a polyisocyanate-reactive composition which contains the major additives such as the blowing agent, the catalyst and the surfactant in addition to the polyisocyanate-reactive component or components.

20 Therefore the present invention also provides a polyfunctional isocyanate-reactive composition which contains the isocyanate-reactive components, the trimerisation catalyst, the carboxylic acid, optionally in combination with the blowing agent, further catalysts and surfactants.

The various aspects of this invention are illustrated, but not limited by the following examples.

25

In these examples the following ingredients are used:

Polyol 1: an aromatic polyester polyol available from Stepan under the name Stepanpol PS 2352

Polyol 2: a sucrose initiated polyether polyol of OH value 155 mg KOH/g

30 Polyol 3: an aromatic amine initiated polyether polyol of OH value 310 mg KOH/g

Polyol 4: an aromatic PET-based polyester polyol

Poyol 5: a sucrose/amine initiated polyether polyol of OH value 585 mg KOH/g

TEP: triethylphosphate

TCPP: tris chloropropyl phosphate

DEEP: diethyl ethyl phosphonate

PEG 300: polyethyleneglycol of MW 300

DC 5357: silicone surfactant available from Air Products

5 DC 193: silicone surfactant available from Air Products

L6900: silicone surfactant available from Crompton OSi

Niax A1: amine catalyst available from Air Products

Jeffcat PMDETA: amine catalyst available from Huntsman Performance Chemicals

Jeffcat TR90: amine catalyst available from Huntsman Performance Chemicals

10 SFB: dimethylcyclohexylamine catalyst (DMCHA) available from Bayer

Catalyst LB: potassium acetate catalyst available from Huntsman Polyurethanes

Dabco K15: potassium 2-ethylhexanoate trimerisation catalyst available from Air Products

Isocyanate: polymeric MDI

15 Example 1

Rigid polyisocyanurate foam panels of varying thickness (indicated between brackets) were prepared at an isocyanate index of 200 % from the ingredients listed in table 1 below.

20 The reaction profile was followed in terms of cream time (CT) which is the time it takes for the foam to start expanding, full cup time (FC) which is the time it takes the rising foam to reach the top-rim of the cup, string time (ST) which is the time it takes to pull the first strings from the foam and end of rise time (ER) which is the time it takes for the foam not to grow anymore in rise-direction.

25 Closed cell content (CCC) of the obtained foam was measured according to standard ASTM D2856 and core density according to standard DIN 5320.

The reaction to fire was measured by the B2 flame spread test according to standard DIN 4102. This is an indicator for the isocyanurate conversion: low isocyanurate conversions result in poor fire performance.

Table 1

Foam No.		1 (4 cm)	2 (10 cm)	3 (20 cm)	4 (10 cm)	5 (20 cm)
Polyol 1	pbw	7.24	7.02	6.66	7.53	7.15
Polyol 2	pbw	4.46	4.32	4.1	4.63	4.4
Polyol 3	pbw	10.03	9.72	9.22	10.42	9.91
TEP	pbw	4.9	4.97	5.12	5.1	5.28
PEG 300	pbw	4.68	4.54	4.3	4.86	4.62
DC 5357	pbw	1.11	1.19	1.23	1.27	1.32
Niax A1	pbw	0.02	0.02	0.02	0.02	0.02
SFB	pbw	0.45	0.43	0.41	0.46	0.44
Dabco K15	pbw	0.67	0.39	0.15	0.67	0.68
Water	pbw	0.94	1.02	1.13	0.81	0.88
Lactic acid	pbw				0.22	0.37
Isocyanate	pbw	65.5	66.38	67.65	64	64.9
CT	sec	9	12	15	12	16
FC	sec	27	37	52	41	56
ST	sec	33	49	73	48	75
ER	sec	55-60	80		85	
CCC	%	86	88	87	88	86
Density	kg/m <sup>3</sup>	41.6	39.8	40.4	42.1	37
B2	cm	13	14	18	13	12

The results given in table 1 indicate that reducing the speed of the system by decreasing the K15 level is detrimental to isocyanurate conversion. However the use of lactic acid in combination with K15 as in foams nos 4 and 5 give enhanced isocyanurate conversion. Using this approach it is possible to achieve the same degree of isocyanurate conversion for slower systems (50 sec string time for 10 cm thickness; 70 sec string time for 20 cm thickness) as it is for fast systems (30 sec string for 4 cm thickness).

Example 2

5 Rigid polyisocyanurate foams were prepared at an isocyanate index of 170 % from the ingredients listed in table 2 below.

Properties were measured as in Example 1 above. The results are presented in Table 2.

Table 2

Foam No.		6	7	8	9
Polyol 5	pbw	29	29	29	29
Polyol 4	pbw	44	44	44	44
TCPP	pbw	20	20	20	20
Water	pbw	2	2	2	2
DMCHA	pbw	1	1	1	1
DC 193	pbw	1	1	1	1
Jeffcat PMDETA	pbw	0.3	0.3	0.3	0.3
Dabco K15	pbw	1.7	1.7		
Catalyst LB	pbw			1.7	1.7
Lactic acid	pbw	1		1.2	
Salicylic acid	pbw		1.7		2.1
Isocyanate	pbw	180	180	180	180
CT	sec	11	15	16	16
FC	sec	22	34	31	37
ST	sec	29	43	36	45
ER	sec	70	85	80	90
Density	g/l	47.5	56.6	45.7	55.9
CCC	%	95.3	93.2	94.2	93.4
B2	cm	8	8.5	8.7	9

Example 3

5 Rigid polyisocyanurate foams were prepared at an isocyanate index of 230 % from the ingredients listed in table 3 below.

Properties were measured as in Example 1 above. The results are presented in Table 3.

Table 3

Foam No.		10
Polyol 4	pbw	84
DEEP	pbw	10
Water	pbw	0.7
Jeffcat TR90	pbw	0.8
L6900	pbw	1.6
Jeffcat PMDETA	pbw	0.2
Dabco K15	pbw	1.2
Catalyst LB	pbw	0.3
Lactic acid	pbw	1.2
n-pentane	pbw	7
Isocyanate	pbw	158
CT	sec	22
ST	sec	85
Density	g/l	36.5
CCC	%	94
B2	cm	12

## CLAIMS

1. Process for preparing rigid urethane-modified polyisocyanurate foam comprising the step  
of reacting an organic polyisocyanate with a polyfunctional isocyanate-reactive  
5 component in the presence of a blowing agent and a trimerisation catalyst characterized in  
that the process is carried out in the presence of a carboxylic acid.
2. Process according to claim 1 wherein the carboxylic acid has a molecular weight below  
250.
3. Process according to claim 1 or 2 wherein the carboxylic acid has a pKa value in water of  
10 between 1 and 5.5.
4. Process according to any one of the preceding claims wherein the carboxylic acid is  
functionalised with at least one additional OH, COOH, SH, NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen  
functional group, wherein R is an alkyl, cycloalkyl or aryl group.
5. Process according to claim 4 wherein the carboxylic acid is functionalised in  $\alpha$  or  $\beta$   
15 position with respect to the carboxyl group.
6. Process according to claim 4 or 5 wherein said functionalised carboxylic acid  
corresponds to the general formula  $X_n - R' - \text{COOH}$  wherein X is OH, COOH, SH,  
NH<sub>2</sub>, NHR, NO<sub>2</sub> or halogen, R' is an at least divalent hydrocarbon moiety, typically an  
at least divalent linear or branched aliphatic hydrocarbon moiety and/or an at least  
20 divalent alicyclic or aromatic hydrocarbon moiety, n is an integer having a value of at  
least 1 and allows for mono and polyfunctional substitution on the hydrocarbon moiety.
7. Process according to claim 6 wherein X is OH or COOH, n is 1 and R' is a linear or  
branched aliphatic or aromatic hydrocarbon having 2 to 6 carbon atoms.
8. Process according to any one of the preceding claims wherein said carboxylic acid is  
25 lactic acid or salicylic acid or maleic acid or acetic acid or malic acid.
9. Process according to any one of the preceding claims wherein said carboxylic acid is used  
in an amount ranging from 0.05 to 5 % by weight based on the isocyanate-reactive  
composition.
10. Process according to any one of the preceding claims wherein the trimerisation catalyst is  
30 a metal salt trimerisation catalyst.
11. Process according to claim 10 wherein the metal salt trimerisation catalyst is an alkali  
metal salt of an organic carboxylic acid.

12. Process according to claim 11 wherein the metal salt trimerisation catalyst is potassium acetate or potassium 2-ethylhexanoate.
13. Process according to any one of claims 10 to 12 wherein the metal salt trimerisation catalyst is used in an amount ranging from 0.5 to 5 % by weight based on the isocyanate-reactive composition.
14. Process according to any one of the preceding claims wherein the reaction is carried out at an isocyanate index of 150 to 450 %.
15. Process according to any one of the preceding claims wherein the blowing agent is water and/or a hydrocarbon and/or a hydrofluorocarbon.
16. Rigid urethane-modified polyisocyanurate foam obtainable by the process as defined in any one of the preceding claims.
17. Polyfunctional isocyanate-reactive composition containing a metal salt trimerisation catalyst and a carboxylic acid.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/09541

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 C08G18/34

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 20059 A (IMPERIAL CHEMICAL INDUSTRIES) 14 May 1998 (1998-05-14) page 1, line 23 -page 7, line 33; claims 1-16; examples ---	1-17
X	EP 0 656 382 A (NISSHINBO INDUSTRIES) 7 June 1995 (1995-06-07) page 2, line 40 -page 10, line 57 page 30, line 23 - line 31 page 31, line 13 - line 19; claims 1,2 ---	1
A	FR 1 228 289 A (IMPERIAL CHEMICAL INDUSTRIES) 29 August 1960 (1960-08-29) page 1, column 2, line 13 -page 2, column 1, line 12; claim 1; examples 2,3 --- -/-	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&amp;\* document member of the same patent family

Date of the actual completion of the international search

10 December 2002

Date of mailing of the international search report

16/12/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Bourgonje, A



## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/09541

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 43 25 014 A (HENKEL) 2 February 1995 (1995-02-02) page 3, line 43 -page 4, line 35; claims 1,2,6; examples -----	1

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/09541

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9820059	A	14-05-1998	AU 729108 B2	25-01-2001
			AU 5118298 A	29-05-1998
			BR 9712729 A	26-10-1999
			CN 1235618 A	17-11-1999
			CZ 9901565 A3	11-08-1999
			DE 69705420 D1	02-08-2001
			DE 69705420 T2	23-05-2002
			DK 935625 T3	01-10-2001
			WO 9820059 A1	14-05-1998
			EP 0935625 A1	18-08-1999
			ES 2158593 T3	01-09-2001
			HU 9904233 A2	28-04-2000
			JP 2001503462 T	13-03-2001
			KR 2000053020 A	25-08-2000
			NZ 335206 A	24-11-2000
			PL 333051 A1	08-11-1999
			RU 2184127 C2	27-06-2002
			SI 935625 T1	31-12-2001
			SK 58199 A3	14-02-2000
			TR 9900971 T2	21-07-1999
			TW 442514 B	23-06-2001
			US 2001006986 A1	05-07-2001
			US 6207725 B1	27-03-2001
EP 656382	A	07-06-1995	JP 3061717 B2	10-07-2000
			JP 7157528 A	20-06-1995
			DE 69412763 D1	01-10-1998
			DE 69412763 T2	14-01-1999
			EP 0656382 A1	07-06-1995
FR 1228289	A	29-08-1960	US 5550168 A	27-08-1996
FR 1228289	A	29-08-1960	GB 879167 A	04-10-1961
			NL 103386 C	
DE 4325014	A	02-02-1995	DE 4325014 A1	02-02-1995